

A PTFE thickened, light viscosity, completely fluorinated grease possessing very wide temperature capability, excellent plastic and elastomer compatibility and resistance to aggressive chemicals.

DaimlerChrysler: MS-9987, GM: 9985880

Lubricant Properties		Typical value	Test Method
Recommended Service Range (°C)		-45 to 225	
Thickener		PTFE	
Base oil	Type	Perfluoropolyether	
	Kinematic viscosity	100°C 40°C	18 cSt 167 cSt
	Viscosity Index		120
	Flash point	°C	> 300
	Pouring point	°C	-48
			Cleveland open cup
			ASTM D-97
Typical Properties of the Grease		Typical value	Test Method
Color, Appearance		White, Smooth	
Penetration (1/10 mm)	Unworked		259
	NLGI Grade		2
	Worked	60X	278
Density		25°C	1.96 g/cm ³
Oil Separation	24 hour(s)	100°C	3.8
Evaporation	24 hour(s)	150°C	0.23 %

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1510)

Distributed by Newgate Simms Limited

Broughton Mills Road, Bretton, Chester, CH4 0BY, United Kingdom
+44(0)1244 660771 www.newgatesimms.com info@newgatesimms.com